



# SEALED SURFACE ADHESIVE

## WALLCOVERING

Technical Data Sheet

Revised: 30/08/2018

### DESCRIPTION

Starch-based ready-to-use adhesive for all types of wallcovering. It can also be used in combination with other Seltex starch-based products.

Ideal for contract wallcoverings.

- Exceptional adhesion strength
- Does not stain
- Suitable for non-absorbent substrates
- Low V.O.C. (Volatile Organic Compounds)
- Antibacterial and anti-mould properties

Suitable for:

- Wide-width contract wallcoverings
- Paper-backed vinyl wallpapers
- Non-woven wallcoverings
- Fibreglass wallcoverings

### SURFACE PREPARATION

Surfaces should be sound, dry, clean and free from damp, dust and grease. Any cracks or holes should be filled and high spots sanded level. We always recommend the use of Seltex Primer.

### PREPARATION OF ADHESIVE

This adhesive is a ready-to-use product however when necessary, dilute it with clean water up to a maximum of 5%.

### APPLICATION

Apply the adhesive in a single coat with a brush or roller. Do not allow adhesive to get onto the face of any wallcovering.

### COVERAGE

Approximately 25 m<sup>2</sup> per 5 kg tub

### CLEANING

Clean possible spills with a damp sponge. The product does not stain.

### CONTRAINDICATIONS

This adhesive is not suitable on damp walls with mould or on surfaces not perfectly prepared. Spillage of the adhesive should be removed immediately.

### PACKAGES

#### 5Kg Bucket

### STORAGE

The product is guaranteed for 24 months from the date of production. Prevent from freezing (keep temperature between 5°C to 40°C)

### TECHNICAL DATA

Base:	starch
Physical appearance:	white cream
pH:	6.5
Viscosity:	60,000 to 80,000 cps
V.O.C.:	zero (0g/l)
Percentage of solid:	about 45%
Customs code:	3506 9190
Application temperature:	between 5°C to 40°C
Waiting time:	0-10 minutes
Open time:	20-30 minutes
Setting time:	48 hours
Non-flammable	

### FINAL PROVISIONS

Keep out of reach of children and pets. Discharge the waste in special containers for building materials.

